



Application		NHL	Typical Mix	Approx Coverage
Internal Plastering	Backing Coats 3/8" Thickness (10mm)	NHL 2	2.5 sand : 1 lime	60 ft ²
	Finishing Coat 1/8" Thickness (3mm)	NHL 2	1.5 Fine Silica sand : 1 Lime	180 ft ²
Stucco/Parging	Coat (10mm) 3/8" Thick	NHL 2	2.5 sand : 1 lime	60 ft ²
		NHL 3.5	2.5 sand : 1 lime	75 ft ²
Pointing Rubble Stone	Depth = Twice the width of the joint	NHL 2	2.5 sand : 1 lime	35-45 ft ²
	Depth = Twice the width of the joint	NHL 3.5	2.5 sand : 1 lime	45-55 ft ²
Pointing Brickwork	Depth = Twice the width of the joint	NHL 2	2.5 sand : 1 lime	65 ft ²
	Depth = Twice the width of the joint	NHL 3.5	2.5 sand : 1 lime	100 ft ²
Harling/Wet Dash/Roughcast		NHL 3.5	2.5 sand/Aggregate : 1 lime	80 ft ²
Bedding Mortar Standard Brick		NHL 2.0 NHL 3.5	2.5 sand: 1 lime	60-75 Bricks 75-100 Bricks
Lime Concrete/ Limecrete	2" Thick per layer (50mm)	NHL5	2 Mixed Aggregate * : 1 Lime	10 ft ²
Approximately 1.6 Cubic Feet per bag when mixed 2 sand to 1 Lime Refer to the Manufacturer for the type of sand needed for each application				